



VISION Rechargeable Products
Sealed Lead Acid Battery

www.vision-batt.com

CTA Series

Front Terminal Battery

The new VISION CTA series of VRLA batteries has been specially designed for use in telecom systems.

You can expect our batteries meet with the standards JIS C8707, DIN, IEC60896-2 & BS6290-4. We have obtained ISO9001, ISO14001 certification. We have obtained UL approval (MH25860) for all types of batteries. We have obtained CE approval for all type of batteries. All these render our batteries to be compatible with requirements of world-level equipments.

With front access terminals, it's easy for installing and taking voltage readings during service.

The battery container and cover, made from V0 class flame retardant ABS & with thick walls, offer the battery with high mechanical strength and safety service features.

Shenzhen Center Power Tech. Co., Ltd

CTA12-80X 12V 80Ah

(Edition Jan 2014)

General Features

- Thick pasted plates with high quality lead-tin-calcium alloy grids for long service life;
- V0 class ABS container and cover, in accordance with flame retardancy standard IEC 707 FV0 for safety operation;
- Centralized venting system for gas ventilation;
- Plastics or rope handles for handling and installation convenience;
- Robust stainless steel stud terminals providing high conductivity, easy connection;
- Design life 12+ years



Dimensions and Weight

	SI Units	English Units
Length	508mm	20.0inch
Width	110mm	4.33inch
Height	231mm	9.09inch
Total Height	231mm	9.09inch
Approx. Weight	31Kg	68.4lbs

Performance Characteristics

- Nominal Voltage 12V
- Number of cell 6
- Nominal Capacity 68°F(20°C)
 - 10 hour rate (8.00A, 10.8V)80.0Ah
 - 5 hour rate (15.0A, 10.5V)75.0Ah
 - 1 hour rate (57.2A, 9.60V)57.2Ah
- Internal Resistance
 - Fully Charged battery 68°F(20°C) ≤ 5.5mOhms
- Self-Discharge
 - 3% of capacity declined per month at 20°C(average)
- Operating Temperature Range
 - Discharge -20~60°C
 - Charge -10~60°C
 - Storage -20~60°C
- Max. Discharge Current 68°F(20°C) 800A(5s)
- Charge Methods: Constant Voltage Charge 68°F(20°C)
 - Cycle use 2.40-2.45VPC
 - Maximum charging current 30% of rated capacity
 - Temperature compensation -30mV/°C
- Standby use 2.20-2.30VPC
 - Temperature compensation -20mV/°C



Center Power Industrial Park, Tongfu Industrial District Dapeng Town, 518120 Shenzhen, China
Tel: 86 755 8431 8088 Fax: 86 755 8431 8038 E-mail: sales@vision-batt.com
Website: <http://www.vision-batt.com>

CTA12-80X 12V 80Ah

Discharge Data

Constant Current Discharge Data (Amperes at 20°C)																								
End Voltage Per cell / V	10min	15min	20min	25min	30min	35min	40min	45min	50min	55min	1h	1.5h	2h	2.5h	3h	4h	5h	6h	7h	8h	9h	10h	12h	24h
1.60	211	166	137	117	101	89.8	80.9	73.0	67.2	61.8	57.2	40.3	31.9	26.8	23.4	19.0	16.1	13.5	11.7	10.4	9.32	8.47	7.31	3.81
1.65	197	153	129	110	97.1	85.3	77.1	69.5	63.7	59.5	56.0	39.5	31.2	26.2	23.0	18.6	15.7	13.3	11.5	10.2	9.18	8.36	7.24	3.78
1.70	180	145	123	105	92.8	82.4	74.1	67.2	62.5	58.3	54.9	38.6	30.6	25.7	22.4	18.1	15.4	13.0	11.3	10.0	9.03	8.24	7.15	3.74
1.75	170	137	116	100	89.1	79.4	71.5	65.6	60.7	56.4	52.9	37.8	29.9	25.1	21.9	17.8	15.0	12.7	11.1	9.90	8.92	8.16	7.05	3.70
1.80	160	131	110	96.0	86.3	77.4	69.8	64.0	59.2	55.0	51.4	37.1	29.3	24.6	21.5	17.4	14.6	12.4	10.8	9.70	8.74	8.00	6.92	3.63

Constant Power Discharge Data (Watts per cell at 20°C)																								
End Voltage Per cell / V	10min	15min	20min	25min	30min	35min	40min	45min	50min	55min	1h	1.5h	2h	2.5h	3h	4h	5h	6h	7h	8h	9h	10h	12h	24h
1.60	365	284	237	202	178	159	145	132	123	114	106	75.2	59.3	50.1	44.0	35.7	30.6	26.1	22.4	20.1	18.0	16.3	14.0	7.19
1.65	337	269	226	195	172	154	140	127	118	110	103	73.3	57.5	49.0	43.4	35.2	30.1	25.5	22.0	19.8	17.8	16.2	13.9	7.16
1.70	313	254	213	185	164	148	136	123	115	108	102	72.2	56.6	48.3	42.7	34.6	29.5	25.1	21.8	19.8	17.7	16.1	13.9	7.12
1.75	292	238	201	177	158	142	130	121	112	106	99.0	70.6	55.8	47.5	42.1	34.2	29.2	24.8	21.4	19.6	17.6	16.0	13.8	7.09
1.80	266	220	189	166	151	136	125	117	109	103	96.0	69.2	54.9	46.8	41.4	33.7	28.7	24.5	21.2	19.3	17.4	15.7	13.6	7.05

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values. All data shall be changed without notice, Vision reserves the right to explain and update the information contained hereinto.

